

# Luxury Vinyl Tiles

Acoustic performance

Extensive colour range

4.5mm thickness for durability

[WWW.TARKOSPEC.COM.AU](http://WWW.TARKOSPEC.COM.AU)

**iD INSPIRATIONS  
LOOSE LAY**

 **Tarkett**

# TECHNICAL DATA SHEET

Certification & classification	Standards	ID Inspirations Loose Lay
Type of floor covering	EN ISO 10582	Compact Resilient Floorcovering
Classification	EN ISO 10874	Domestic: 23 Commercial: 33 Industrial: 42
Technical characteristics		
Total thickness	EN ISO 24346	4.5 mm
Wear layer thickness	EN ISO 24340	0.55 mm
Total weight	EN ISO 23997	7.3 kg/m <sup>2</sup>
Wear layer binder content	EN ISO 10582	Type I
Dimensions	EN ISO 24342	Planks 229 x 1219 mm 10 planks/box = 2.79 m <sup>2</sup>
Surface treatment (PUR)		Yes
Beveled edges		No
Technical performances		
Dimensional stability	EN ISO 23999	≤ 0.10%
Reaction to fire	ISO AS 9239-1	Critical radiant flux 9.1 kW/m <sup>2</sup> Smoke 172 %.min
Residual indentation	EN ISO 24343-1	≤ 0.10 mm
Furniture leg	EN 424	No damage
Castor chair	ISO 4918 (EN 425)	No damage
Impact sound reduction	EN ISO 717-2	ΔLw 8 dB
Thermal resistance	EN ISO 10456	0.04 m <sup>2</sup> K/W
Light fastness	EN ISO 105-B02	≥ 6
Chemical resistance	EN ISO 26987	High Resistance
Slip resistance	AS 4586/ DIN 51130*	R9 / P2
Electrical properties	EN 1081	ca. 10 <sup>11</sup> Ohm

\* DIN 51130.2004 and 2010 is equivalent to Appendix D AS 4586.2013

The above information is subject to modification for the benefit of further improvement. (09/18).

Tarkett's instructions regarding installation, cleaning and maintenance should be observed. Please contact Tarkett at the address shown for these instructions.



Disclaimer: Please note that products in photos are installed for creative purposes and not according to technical specifications. Please refer to Tarkett installation instructions for guidance.

Contact: Tarkett Australia  
P: 1300 851 484  
E: customerservice@tarkett.com  
W: www.tarkospec.com.au

